

**TEST REPORT**

Client: Gabriel
Hjulgagervej 55
Postbox 59
DK-9100 Aalborg
Denmark

Entry No: 73682

Date received: 11/02/2016

Client's Description: Sample of fabric: Fighter 60082 Light Grey

Test Required: Seam Slippage and Colour Fastness to Water Spotting^s

Conditioning: In accordance with BS EN ISO 139: 2005 for a minimum of 24 hours at 65+/-4%, Relative Humidity, 20+/-2°C

Date Tests Completed: 23/02/2016

Seam Slippage: BS EN ISO 13936-2: 2004

	<u>Mean Seam opening</u>
Warp Way Seam	3 mm
Weft Way Seam	3 mm

Colour Fastness to Water Spotting: BS EN ISO 105-E16:2007 ^s

	<u>Grade</u>
Inner circle of tested area :	5
Outer periphery of tested area:	5

None: The water absorbed after 30 minutes.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein



Vivienne Brockbank
Senior Technician
23 February 2016

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
 - ❖ Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104